

Winch Anchor Grout

Purpose

A high-speed grout for use underground in mines, bolt-holes or any area where quick setting and high early strength is of utmost importance.

Mixing

Mix 5.6 litres water with 20kg Winch Anchor Grout to a slurry. Final volume should be 12.4 litres grout.

Use all mixed material within 6 minutes of mixing.

Winch Anchor Grout attains a treacle-like consistency when mixed and has self-levelling properties for easy placing.

Setting time

Ready for normal loading in 90 minutes from pouring.

Strength

90 minutes 13.5 mPa

1 day 18.7 mPa

2 days 23.1 mPa

7 days 26.3 mPa

28 days 28.3 mPa

Packaging

Available in 20 kg paper bags.

Technical Information

Cemcrete provides a free comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology.

Head Office
8 Telford Street, Industria
Tel. (011) 474-2415
Fax (011) 474-2416
info@cemcrete.co.za
www.cemcrete.co.za

Gauteng; Mpumulanga
Gareth Beaven
082 566-3107
gareth@cemcrete.co.za

North West Province;
Limpopo; Botswana;
Mozambique
Andre van Eck
083 305-6313
andreve@cemcrete.co.za

Kwa-Zulu Natal; Free State
Dave Rose
082 894-4635
Tel./Fax (031) 903-1374
dave@cemcrete.co.za

Eastern, Western &
Northern Cape; Namibia
Sean Cloete
073 251-4861
Tel. (021) 911-0200
Fax (021) 930-2738
sean@cemcrete.co.za