

Mould Rubber

Description

A synthetic latex rubber for detailed reproduction of objects of virtually any fine texture.

Types

One type only, but can be mixed with fillers and fibres to thicken and strengthen.

Limitations

Final product cannot take excessive heat with regard to the material being cast.

Site Work

Storage

Shelf life about 12 months, but must be kept in a totally airtight container. Will thicken if volatiles are allowed to evaporate.

Surface preparation

Surfaces to be clean, dry and free of loose material.

Weather

Work in dry conditions, final set product is resistant to water.

Application

Apply 3 or 4 coats of the neat Mould Rubber by fine bristle brush letting each coat dry completely between coats. This is to fill the fine detail of the work being copied.

Mixing

Mix with Cemcrete's "Mould Rubber Thickener" and/or loose Polypropylene fibre until thick enough not to sag and run.

Reinforcing

CemForce, a polypropylene woven mat can be cut to shape and set into "wet thickened" Mould Rubber which will remarkably strengthen the final moulding. If the mould will need stretching off the object being moulded, do not reinforce in this manner. Therefore ideal for flat mouldings only.

Curing

Allow to thoroughly dry before carefully peeling of substrate and dust with dry Cemcrete's Mould Rubber Thickener before use.

Packaging

Mould Rubber	1 litre and 5 litre tins
Mould Rubber Thickener	1 kg sacks
Polypropylene fibre 6mm	1kg plastic bag
Cemforce	1m widths, any length

Technical Information

Cemcrete provides a free comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology.

Head Office
8 Telford Street, Industria
Tel. (011) 474-2415
Fax (011) 474-2416
info@cemcrete.co.za
www.cemcrete.co.za

Gauteng; Mpumalanga
Gareth Beaven
082 566-3107
gareth@cemcrete.co.za

North West Province;
Limpopo; Botswana;
Mozambique
Andre van Eck
083 305-6313
andreve@cemcrete.co.za

Kwa-Zulu Natal; Free State
Dave Rose
082 894-4635
Tel./Fax (031) 903-1374
dave@cemcrete.co.za

Eastern, Western &
Northern Cape; Namibia
Sean Cloete
073 251-4861
Tel. (021) 911-0200
Fax (021) 930-2738
sean@cemcrete.co.za