

## Permastop continued...

**Membrane:** Lay impregnated membrane over area to be covered and use paint brush to smooth out and flatten membrane.

**Gushing Leaks:** Open concrete at place where water is pouring out to a cavity of about 40 mm<sup>3</sup>. Grout in place a piece of old hose pipe using "Joint Filling Mix" mixed with Permastop Accelerator instead of only water. Once water has been lead away from surface of concrete, continue to waterproof rest of concrete. When set and all is waterproofed except water flowing from pipe, remove pipe by twisting and immediately fill with a plug of jointing mix mixed with the accelerator. Use rubber gloves if contact with skin is expected.

### Curing

In hot dry conditions cure completed work by damping with clean water three times during the day following the day of application. Protect against freezing for 24 hours. Protect from direct sun and wind by covering with plastic or wet hessian for 24 hours.

### Painting

If Permastop is to be subsequently painted, it should be cured by wetting for at least 15 days. Neutralise by applying to surface a mixture of 8 volumes water and 1 volume hydrochloric acid or vinegar. Allow to react for 15 minutes. Rinse thoroughly, allow to dry, then paint.

**Always wear gloves when applying Permastop**

### Coverage

Brush application: Approximately 1,3m<sup>2</sup>/kg/coat depending upon suction and texture of surface.

Joint filling: Depends on size of joint.

With polypropylene membrane: Approximately 3 kg/m<sup>2</sup>.

### Packaging

Permastop: In 1 kg, 5 kg and 25 kg non-returnable drums.

Accelerator: In 1 litre and 5 litre non-returnable drums.

Membrane: In 100 mm x 10m and 1000 mm x any lengths.  
In 200 mm x 10m and 1000 mm x any lengths.  
In 300 mm x 10m and 1000 mm x any lengths.

### Technical Information

Cemcrete provides a free comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology.

Head Office  
8 Telford Street, Industria  
Tel. (011) 474-2415  
Fax (011) 474-2416  
info@cemcrete.co.za  
www.cemcrete.co.za

Gauteng; Mpumulanga  
Gareth Beaven  
082 566-3107  
gareth@cemcrete.co.za

North West Province;  
Limpopo; Botswana;  
Mozambique  
Andre van Eck  
083 305-6313  
andreve@cemcrete.co.za

Kwa-Zulu Natal; Free State  
Dave Rose  
082 894-4635  
Tel./Fax (031) 903-1374  
dave@cemcrete.co.za

Eastern, Western &  
Northern Cape; Namibia  
Sean Cloete  
073 251-4861  
Tel. (021) 911-0200  
Fax (021) 930-2738  
sean@cemcrete.co.za