

Plaster Cote

March 2010

Description

A specially designed cement-based plaster mixture for rapid thin application to brickwork and blockwork to fill the joints and other imperfections economically.

Purpose

To provide a level base for the application of Cemcrete's CemWash, Thermoplastic Coating, StippleCrete, Texturite Roughcast to walls constructed with bricks or blocks.

Types

One type only.

Applications

Recommended for affordable housing to dispense with expensive conventional plastering.

Specifying

Cemcrete's Plaster Cote as a leveling base coat for the final finishing coat.

Site Work**Storage**

In unopened sacks on slats in a dry shed for 3 months.

Surface Preparation**• New brickwork**

No preparation except damping down the clean hard masonry.

• Previously coated work

Surfaces previously coated should be chipped thoroughly and wire brushed to remove all loose material. When dry the surface should be slushed with a solution of 1 volume CemBond and 3 volumes water mixed with neat cement and allowed to dry for a minimum of 2 hours.

Mixing

Plaster Cote should be mixed with a solution of 1 volume CemBond and 5 volumes water.

Application

The mixture in the bucket should be sloppy and pourable. Hold the steel float against the wall at 45° and using a miller's scoop pour the mixed slurry between the trowel and the wall at the same time moving the trowel upwards so that the slurry fills the joints and imperfections but does not build up a thickness of plaster greater than 2mm on the bricks. After allowing a short setting time the surface should be wood floated.

Curing

Cure all completed Plaster Cote by wetting with clean water three times the next day.

Specimen Finish

A trial area should be treated on site for the architect's approval.

Coverage

Approximately 10m² per 40kg sack if not exceeding 2mm thick and 1.5 litre concentrated CemBond.

Packaging

Plaster Cote is available in 40kg paper bags.

CemBond is available in 1 litre, 5 litre, and 20 litre plastic containers.

Technical Information

Cemcrete provides a free comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology.

Head Office
8 Telford Road, Industria
PO Box 43236, Industria, 2042
Tel. (011) 474-2415
Fax (011) 474-2416

0860 cemcrete
info@cemcrete.co.za
www.cemcrete.co.za