

# CreteSeal-Solvent Based Datasheet

January 2017

Page 1 of 2

A novel and innovative PU Pre-polymer based moisture solvent based interior, exterior satin sheen finish for uncoated slasto, floor tiles, cement screeds, concrete stone and masonry floor surfaces to protect substrates from rain/sun and heavy duty wear and tear.

## Technical Data

Type	PU/Pre polymer
Colour	Transparent
Pot life	Skins at early stages
Initial set	12 hours
Final cure	7-10 days
Working time after mixing	30 minutes
Application temperature (ambient)	5°C-30°C
Substrate temperature	5°C-30°C
pH scale	Acidic
UV resistance	Stable and non-yellowing
Abrasive resistance	Trafficable after 7-10 days at 25°C and 50% RH
Density	0.8kg/litre
Protection during application	Use sun and wind barriers
Safety	See MSDS

## Product Features

- Impedes fungal growth
- Excellent adhesion to range of properly prepared slasto, tile and masonry/cement floor substrates
- Reduces the chance of efflorescence and water absorption
- High lights the natural colour of tiles, screeds and slasto
- Excellent chemical resistance against a range of domestic/light industrial chemicals stops staining of the tiles, slasto especially around braai areas

## Application Areas

- Low and high density cement screeds, with sufficient porosity
- Slasto, stone and uncoated tiles

## Specimen finish

A trial area should be treated on-site for the architect's approval and suitability.

## Surface Preparation

Surfaces should be clean, hard and dry at the time of application. For uncoated dry concrete, cement screeds, stone, slasto and tile surfaces. Remove all dust, foreign material, fungal, algae growth - fill and seal all visible cracks.

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.

# CreteSeal-Solvent Based Datasheet

January 2017

Page 2 of 2

## Application Procedure

---

- The first coat must be applied to the dry substrate using an 'Addis' primer and undercoat roller and be allowed to dry completely until it is tack free before applying the second coat, normally a minimum of 6-8 hours at 24 degrees
- The second coat must be applied at a 90 degree angle to the first coat
- A 3rd coat may be necessary depending on the initial substrate porosity
- Clean up application equipment with Xylene
- Apply water droplets to various parts of the floor. If water is absorbed, apply additional suitable coats
- Ensure no pooling of the sealer is left on the surface during application
- Only apply in ventilated areas, keep away from all ignition sources, flames and sparks. Do not eat, drink or smoke while applying this product.

## General

---

- Do not apply before 9am or after 4pm in the winter
- Do not apply to exterior surfaces if rain appears imminent within 4-6 hours of application
- Although the spreading rate will vary with porosity and type of substrate. For uncoated new surfaces work on 10-12m<sup>2</sup>/L for the first coat and 12-14m<sup>2</sup>/L for subsequent coats.
- Clean all application equipment with Xylene.
- This sealer is ready for use un-thinned, thinning will reduce its effectiveness. Curing membranes and shutter release agents should be completely removed prior to the commencement of work.
- Apply as many thin coats as is needed to achieve an even sheen across the surface for best results.
- **CreteSeal-Solvent Based** must be allowed to dry completely, normally 24-48 hours, before it is subjected to temperatures below 6 degrees or to water from any source, such as hoses, sprinklers, condensation, or rain.
- After the sealer is completely dry, the area may only be opened to light use within the first seven days after application. The sealer gains strength after this period.

## Coverage

---

Although the spreading rate will vary with porosity and type of substrate. For uncoated new surfaces work on 10-12m<sup>2</sup>/L for the first coat and 12-14m<sup>2</sup>/L for subsequent coats.

## Precautions

---

- This products non Flammable Flash Point circa is 37°C.
- See MSDS for further details.
- Once opened **CreteSeal-Solvent Based** needs to be used up within two days. The sealer is sealed with nitrogen in the tin and once opened and exposed to air it will start to gel.

## Packaging

---

Available in 1 L and 5 L containers only

## Limitations

---

**CreteSeal-Solvent Based** must only be used onto properly dried substrates with a moisture content less than 5%. Damp objects may cause discoloration. **CreteSeal-Solvent Based** must not be used in areas subject to water submersion or concentrated and extended periods of abrasion and scratching such as from metal wheeled chairs and trollies etc. Where this is the case use protective carpet foot pads to prevent scratching.

## Storage

---

Shelf life is 12 months from date of invoice. Should the can be compromised or damaged the contents will begin to gel and solidify from bottom to top.

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.